

# American White Ash

*Fraxinus Americana*

Similar in appearance to European ash. The sapwood is light coloured to nearly white and the heartwood varies from greyish brown to pale yellow streaked with brown. The wood is generally straight-grained with a coarse, uniform texture. Also known as Northern Ash, Southern Ash, White Ash.

## Application Suitability

Furniture • Cabinetry • Joinery • Flooring • Boating

Density	675	Hardness (janka) (kN)	6.0	Stability	Good
Specific Gravity	0.60	Finish	Excellent	Durability	Non Durable
Modulus of Rupture (Mpa Dry)	104	Gluing	Good	Screwing Split Resistance	Good
Modulus of Elasticity (Gpa Dry)	12	Machining	Good	Nailing Split Resistance	Good
Radial Shrinkage	4%	Sapwood Lyctid susceptible	Yes	Growing region	North America
Tangential Shrinkage	7%			Availability	Widely

BT Tasmania  
(03) 6452 2522  
3 Brittons Road  
Smithton, TAS 7330

BT New South Wales  
(02) 8783 9900  
116-118 Jemma Road  
Prestons, NSW 2170

BT Queensland  
(07) 3888 3351  
100 Potassium Street  
Narangba, QLD 4504

BT Victoria  
(03) 8769 7111  
25 Gaine Road  
Dandenong, VIC

BT International  
+61 2 8783 9900  
116-118 Jemma Road  
Prestons, NSW 2170

BT Veneer Products  
03 6435 1108  
2 Elizabeth St  
Somerset TAS 7322

