

Celery Top Pine

Phyllocladus Asplenifolius, Phyllocladus Rhomboidalis

The heartwood colour is pale yellow, with clearly defined growth rings. It is straight grained, with a fine, even texture. No taste or odour. Also known as Celery Top, Tasmanian Celery Top Pine.

Application Suitability

Furniture • Cabinetry • Joinery • Flooring • Decking & Cladding • Boating

Density	650	Hardness (janka) (kN)	4.5	Stability	Excellent
Specific Gravity	0.64	Finish	Excellent	Durability	Durable
Modulus of Rupture (Mpa Dry)	98	Gluing	Good	Screwing Split Resistance	Excellent
Modulus of Elasticity (Gpa Dry)	10	Machining	Excellent	Nailing Split Resistance	Excellent
Radial Shrinkage	1.5%	Sapwood Lyctid susceptible	No	Growing region	Tasmania
Tangential Shrinkage	3.5%			Availability	Available

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Veneer Products
03 6435 1108
2 Elizabeth St
Somerset TAS 7322



brittontimbers.com.au

