

Huon Pine

Dacrydium Franklinii

Heartwood pale straw, becoming yellow after long exposure. Sapwood very narrow and hard to distinguish. Texture very fine and even. Grain straight. Growth rings closely spaced. A characteristic odour, due to the essential oil methyl eugenol, present when wood freshly cut. Material with a birds-eye figure is sometimes obtainable.

Application Suitability

Furniture • Cabinetry • Joinery • Boating

Density	520	Finish	Excellent	Stability	Excellent
Radial Shrinkage	2.5%	Gluing	Fair	Durability	Durable
Tangential Shrinkage	3%	Machining	Excellent	Screwing Split Resistance	Excellent
		Sapwood Lyctid susceptible	No	Nailing Split Resistance	Excellent
				Growing region	Tasmania
				Availability	Limited

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Veneer Products
03 6435 1108
2 Elizabeth St
Somerset TAS 7322

