

Rock Maple

Acer Saccharum

The sapwood is creamy white with a slight reddish brown tinge and the heartwood varies from light to dark reddish brown. The amount of darker brown heartwood varies. Can contain pith fleck. The wood has a close, fine texture and is generally straight grained, but also occurs as "curly", "fiddleback", and "birds-eye". Also known as Sugar Maple, Rock Maple, Black Maple.

Application Suitability

Furniture • Cabinetry • Joinery • Flooring • Boating

Density	705	Hardness (janka) (kN)	6.0	Stability	Good
Specific Gravity	0.63	Finish	Excellent	Durability	Non Durable
Modulus of Rupture (Mpa Dry)	109	Gluing	Good	Screwing Split Resistance	Fair
Modulus of Elasticity (Gpa Dry)	13	Machining	Good	Nailing Split Resistance	Fair
Radial Shrinkage	3%	Sapwood Lyctid susceptible	Yes	Growing region	North America
Tangential Shrinkage	6%			Availability	Widely

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Veneer Products
03 6435 1108
2 Elizabeth St
Somerset TAS 7322

