

Spotted Gum Quarter Cut

Corymbia Maculata, Corymbia Citroedora, Eucalyptus Henryi

Heartwood pale to dark brown or chocolate. Sapwood is distinctively paler but there maybe a zone of intermediate wood. Texture moderately coarse. Grain variable, the frequent presence of wavy grain produces an attractive fiddleback figure. Slightly greasy nature. Gum veins common. Northern material is usually slightly denser, stronger and more durable than southern. Also known as Lemon Scented Gum.

Application Suitability

Furniture • Cabinetry • Joinery • Flooring • Decking & Cladding

Density	950	Hardness (janka) (kN)	11.0	Stability	Fair
Specific Gravity	0.95	BAL	29.0	Durability	Durable
Modulus of Rupture (Mpa Dry)	150	Finish	Good	Screwing Split Resistance	Good
Modulus of Elasticity (Gpa Dry)	23	Gluing	Poor	Nailing Split Resistance	Good
Radial Shrinkage	4.5%	Machining	Good	Growing region	Australia
Tangential Shrinkage	6%	Sapwood Lyctid susceptible	Yes	Availability	Available

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Veneer Products
03 6435 1108
2 Elizabeth St
Somerset TAS 7322