

Tasmanian Oak Crown Cut

Eucalyptus Obliqua

Heartwood pale to light brown in colour with a pinkish tinge. Sapwood is pale yellow, usually distinguishable from the heartwood. Texture moderately coarse but even. Grain sometimes interlocked. Growth rings visible but not prominent. Gum veins are common. Also known as Messmate.

Application Suitability

Flooring • Furniture • Cabinetry • Joinery • Boating

Density	780	Hardness (janka) (kN)	5.7	Stability	Good
Specific Gravity	0.78	Finish	Good	Durability	Non Durable
Modulus of Rupture (Mpa Dry)	118	Gluing	Good	Screwing Split Resistance	Good
Modulus of Elasticity (Gpa Dry)	15	Machining	Good	Nailing Split Resistance	Good
Radial Shrinkage	3.50	Sapwood Lyctid susceptible	Yes	Growing region	Tasmania
Tangential Shrinkage	6			Availability	Widely

BT Tasmania
(03) 6452 2522
3 Brittons Road
Smithton, TAS 7330

BT New South Wales
(02) 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Queensland
(07) 3888 3351
100 Potassium Street
Narangba, QLD 4504

BT Victoria
(03) 8769 7111
25 Gaine Road
Dandenong, VIC

BT International
+61 2 8783 9900
116-118 Jemma Road
Prestons, NSW 2170

BT Veneer Products
03 6435 1108
2 Elizabeth St
Somerset TAS 7322

