TASMANIAN OAK **FLOORING**

Eucalyptus Obliqua

Britton's Tasmanian Oak flooring has a reputation in Australia and internationally as a durable, stable and attractive product. Tasmanian Oak is a warm, dense and resilient timber. As a flooring choice, Britton's Tasmanian Oak is without peer.

Harvested from the sustainably-managed and PEFC certified temperate forests of the north-west region of the state, Tasmanian Oak's light shades of pale straw to light brown make it a favourite with architects, builders and designers who are looking to inject a modern, crisp feel to their building and design projects.

Tasmanian Oak flooring is machined and dried at Britton's state-of-the-art Tasmanian mill to ensure hard-wearing and high impact resistance which makes it particularly suitable where durability and strength are paramount.

Britton Timbers carries stocks of sustainably harvested Tasmanian Oak and distributes nationally. Britton Timbers International handles shipping to overseas destinations.

Board Widths: Up to 160mm (wider boards on request) Covers: 12mm Overlay - 65x12, 85x12, 108x12, 133x12

Secret Nailing, End-Matched: 65x19,65x21,85x19,108x19,133x19,160x19









TECHNICAL INFORMATION

| Density (kg/m3 dry) | 780 | Tangential Shrinkage % | 6.5 | Machining | Good |
|---------------------------------|------|----------------------------|---------|---------------------------------|--------|
| Specific Gravity | 0.78 | Hardness (Janka) (kN) | 5.7 - 7 | Resistance to Split in Nailing | Good |
| Modulus of Rupture (MPa dry) | 118 | Finish | Good | Resistance to Split in Screwing | Good |
| Modulus of Elasticity (GPa dry) | 15 | Stability | Good | Gluing | Good |
| Radial Shrinkage % | 3.5 | Sapwood Lyctid Susceptible | Yes | Growing Region | TAS |
| | | | | Availability | Widely |





E dominic@brittontimbers.com.au

+61 2 8783 9800

M +61 438 878 307



