

DRY GRADING GUIDELINES

Tasmanian Oak

110 & 135 X 19 Window Reveals

To be graded on best face and ½ of edges.

| Prime Grade | |
|--------------------------------|---|
| Minimum length | 0.9 metres |
| Burls | Unlimited |
| Sapwood | Unlimited |
| Stain | Slight |
| Black speck | Slight |
| Tight gum vein | Less than ¼ length and 2mm wide, except within 25mm of 1 edge when it may extend full length of board |
| Loose gum vein | Not on best face |
| Hobnail | Unlimited |
| Gum pockets | Not on best face |
| Back sawn gum vein | Slight |
| Surface checks | Not on best face |
| Knots | Not on best face |
| Wane | Nil on best face and minimal on back |
| Want | Nil on best face and minimal on back |
| Grub holes | Nil |
| Pinholes | 1 per metre |
| Primary or dry rot | Nil |
| End splits | Less than 10 mm |
| Heart & heart shake | Nil on best face |
| Hit & miss | Slight and not on best face |