

E. obliqua immature

E. obliqua immature

Meter reading	06	07	08	09	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	
Wood Temp °C	Corrected Moisture Content for Species & Temperature																							
05	08	09	10	12	13	14	15	16	17	18	20	21	22	23										
10	08	09	10	11	12	13	14	15	17	18	19	20	21	22	23									
15	07	08	09	10	12	13	14	15	16	17	18	19	20	21	23									
20	07	08	09	10	11	12	13	14	15	16	17	18	19	20	21	22	23							
25		07	08	09	10	11	12	13	14	15	16	17	18	19	20	21	22	23						
30		07	08	09	10	11	12	13	13	14	15	16	17	18	19	20	21	22	23					
35			07	08	09	10	11	12	13	14	15	16	17	17	18	19	20	21	22	23				
40				07	08	09	10	11	12	13	14	15	16	17	17	18	19	20	21	22	23			
50					07	08	09	10	11	12	12	13	14	15	16	17	18	19	20	20	21	22	23	
60						07	08	09	09	10	11	12	13	14	15	15	16	17	18	19	20	21	21	
70							07	08	09	10	11	12	12	13	14	15	16	17	17	18	19	20		
80								07	08	09	10	10	11	12	13	14	14	15	16	17	18	19		
90									07	08	09	09	10	11	12	12	13	14	15	16	16	17		



© TTPB 2000

with compliments

Timber Research Unit
 School of Architecture, University of Tasmania,
 Locked Bag 1-324, Launceston, Tas, 7250

phone: 03 6324 3133 fax: 03 6324 3141
 email: Timber@arch.utas.edu.au
 web: <http://www.tastimber.tas.gov.au>