

Meter reading	06	07	08	09	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	
Wood Temp °C	Corrected Moisture Content for Species & Temperature																							
05	08	09	10	11	12	13	14	14	15	16	18	18	19	20										
10	08	09	10	11	11	12	13	14	15	16	17	18	18	19	20									
15	07	08	09	10	11	12	13	14	14	15	16	17	18	18	20									
20	07	08	09	10	11	11	12	13	14	14	15	16	17	18	18	19	20							
25		07	08	09	10	11	11	12	13	14	15	16	17	18	18	19	20							
30		07	08	09	10	11	11	12	12	13	14	14	15	16	17	18	18	19	20					
35			07	08	09	10	11	11	12	13	14	14	15	15	16	17	18	18	19	20				
40				07	08	09	10	11	11	12	13	14	14	15	15	16	17	18	18	19	20			
50					07	08	09	10	11	11	11	12	13	14	14	15	16	17	18	18	18	19	20	
60						07	08	09	09	10	11	11	12	13	14	14	14	15	16	17	18	18	18	
70							07	08	09	10	11	11	11	12	13	14	14	15	15	16	17	18		
80								07	08	09	10	10	11	11	12	13	13	14	14	15	16	17		
90									07	08	09	09	10	11	11	11	12	13	14	14	14	15		



with compliments

Timber Research Unit
 School of Architecture, University of Tasmania,
 Locked Bag 1-324, Launceston, Tas, 7250

phone: 03 6324 3133 **fax:** 03 6324 3141
email: Timber@arch.utas.edu.au
web: <http://www.tastimber.tas.gov.au>