

AMERICAN ASH



APPLICATIONS
FURNITURE CABINETS JOINERY FLOORING BOATING

DENSITY
675

REGION
NORTH AMERICA

Similar in appearance to European ash. The sapwood is light coloured to nearly white and the heartwood varies from greyish brown to pale yellow streaked with brown. The wood is generally straight-grained with a coarse, uniform texture. Also known as Northern Ash, Southern Ash, White Ash.



PROPERTIES

DENSITY 675	MODULUS OF RUPTURE (MPA DRY) 104	RADIAL SHRINKAGE 4%
HARDNESS (JANKA) (KN) 6.0	FINISH EXCELLENT	DURABILITY NON DURABLE
MACHINING GOOD	SCREWING SPLIT RESISTANCE GOOD	NAILING SPLIT RESISTANCE GOOD
GLUING GOOD	GROWING REGION NORTH AMERICA	SPECIFIC GRAVITY 0.60
MODULUS OF ELASTICITY (GPA DRY) 12	TANGENTIAL SHRINKAGE 7%	STABILITY GOOD
AVAILABILITY WIDELY	SAPWOOD LYCTID SUSCEPTIBLE YES	