

# AMERICAN BLACK WALNUT



**APPLICATIONS**  
FURNITURE CABINETRY JOINERY FLOORING BOATING

**DENSITY**  
609

**REGION**  
NORTH AMERICA

The sapwood is creamy white, heartwood is light brown to dark chocolate brown, occasionally with a purplish cast and darker streaks. Walnut can be supplied steamed, to darken sapwood or left unsteamed. Generally straight grained, but sometimes has attractive wavy or curly grain. Also known as Black Walnut, American Walnut.



## PROPERTIES

<b>DENSITY</b> 609	<b>MODULUS OF RUPTURE (MPA DRY)</b> 100	<b>RADIAL SHRINKAGE</b> 3%
<b>HARDNESS (JANKA) (KN)</b> 5.0	<b>FINISH</b> EXCELLENT	<b>DURABILITY</b> NON DURABLE
<b>MACHINING</b> EXCELLENT	<b>SCREWING SPLIT RESISTANCE</b> GOOD	<b>NAILING SPLIT RESISTANCE</b> GOOD
<b>GLUING</b> GOOD	<b>GROWING REGION</b> NORTH AMERICA	<b>SPECIFIC GRAVITY</b> 0.55
<b>MODULUS OF ELASTICITY (GPA DRY)</b> 11	<b>TANGENTIAL SHRINKAGE</b> 4%	<b>STABILITY</b> GOOD
<b>AVAILABILITY</b> WIDELY	<b>SAPWOOD LYCTID SUSCEPTIBLE</b> YES	