

AMERICAN TULIPWOOD



APPLICATIONS
FURNITURE JOINERY CABINETRY

DENSITY
449

REGION
NORTH AMERICA

Tulipwood similar in grain characteristic like maple being straight grained with medium to fine texture. The sapwood is creamy white whereas the heartwood can vary from pale yellow or brown and even green to purple in extreme cases. The wood darkens with time on exposure to UV light and the green colour will turn brown.



PROPERTIES

DENSITY 449	MODULUS OF RUPTURE (MPA DRY) 70	RADIAL SHRINKAGE 4.6%
HARDNESS (JANKA) (KN) 2.4	FINISH EXCELLENT	DURABILITY NON DURABLE
MACHINING EXCELLENT	SCREWING SPLIT RESISTANCE GOOD	NAILING SPLIT RESISTANCE GOOD
GLUING GOOD	GROWING REGION NORTH AMERICA	SPECIFIC GRAVITY 0.42
MODULUS OF ELASTICITY (GPA DRY) 11	TANGENTIAL SHRINKAGE 8.2%	STABILITY GOOD
AVAILABILITY AVAILABLE	SAPWOOD LYCTID SUSCEPTIBLE YES	