

AMOORA



APPLICATIONS

FURNITURE CABINETS JOINERY FLOORING

DENSITY

700

REGION

ASIA PACIFIC

Sapwood is straw coloured and is sharply differentiated from the heartwood, which is brick red or dark red when fresh, darkening to dark red brown or walnut brown on exposure. Grain is interlocked or irregular. Texture is slightly coarse and even. Also known as Bekak.



PROPERTIES

DENSITY

700

HARDNESS (JANKA) (KN)

7.0

MACHINING

FAIR

GLUING

GOOD

MODULUS OF ELASTICITY (GPA DRY)

17

AVAILABILITY

AVAILABLE

MODULUS OF RUPTURE (MPA DRY)

117

FINISH

EXCELLENT

SCREWING SPLIT RESISTANCE

FAIR

GROWING REGION

ASIA PACIFIC

TANGENTIAL SHRINKAGE

2.5%

SAPWOOD LYCTID SUSCEPTIBLE

YES

RADIAL SHRINKAGE

2.5%

DURABILITY

DURABLE

NAILING SPLIT RESISTANCE

EXCELLENT

SPECIFIC GRAVITY

0.70

STABILITY

GOOD