

AUSTRALIAN CHESTNUT



APPLICATIONS
FURNITURE CABINETS JOINERY FLOORING

DENSITY
800

REGION
AUSTRALIA

Flooring is characterised by subtle colour variations from mellow straw brown to light chocolates. Durable eucalypts are blended to provide a sophisticated, natural beauty to any interior. Also known as Southern Blackbutt, Chestnut.



PROPERTIES

DENSITY 800	MODULUS OF RUPTURE (MPA DRY) 118	RADIAL SHRINKAGE 3.5%
HARDNESS (JANKA) (KN) 8.0	FINISH GOOD	DURABILITY DURABLE
MACHINING GOOD	SCREWING SPLIT RESISTANCE GOOD	NAILING SPLIT RESISTANCE GOOD
GLUING GOOD	GROWING REGION AUSTRALIA	SPECIFIC GRAVITY 0.80
MODULUS OF ELASTICITY (GPA DRY) 15	TANGENTIAL SHRINKAGE 6%	STABILITY GOOD
AVAILABILITY WIDELY	SAPWOOD LYCTID SUSCEPTIBLE NO	