

# AUSTRALIAN WORMY CHESTNUT



APPLICATIONS  
FURNITURE CABINETRY JOINERY FLOORING

DENSITY  
800

REGION  
AUSTRALIA

Trees are affected by wildfires, years of drought and attack by insects. Flood and strong winds stunt their growth with each piece showing nature's signature. Deep red gum veins formed by fire, ambrosia beetle marks, pin holes and squiggly worm marks are all evident. Also known as Southern Blackbutt, Chestnut.



## PROPERTIES

DENSITY 800	MODULUS OF RUPTURE (MPA DRY) 118	RADIAL SHRINKAGE 3.5%
HARDNESS (JANKA) (KN) 8.0	FINISH GOOD	DURABILITY DURABLE
MACHINING GOOD	SCREWING SPLIT RESISTANCE GOOD	NAILING SPLIT RESISTANCE GOOD
GLUING GOOD	GROWING REGION AUSTRALIA	SPECIFIC GRAVITY 0.80
MODULUS OF ELASTICITY (GPA DRY) 15	TANGENTIAL SHRINKAGE 6%	STABILITY GOOD
AVAILABILITY AVAILABLE	SAPWOOD LYCTID SUSCEPTIBLE NO	