

BLACKBUTT



APPLICATIONS
FURNITURE CABINETRY JOINERY FLOORING DECKING & CLADDING

DENSITY
900

REGION
AUSTRALIA

Heartwood pale brown, but northern material may sometimes display a slight pinkish tinge. Sapwood distinctively paler. Texture medium and even. Grain usually straight. Gum veins are common.



PROPERTIES

DENSITY
900

HARDNESS (JANKA) (KN)
9.0

MACHINING
GOOD

GLUING
POOR

MODULUS OF ELASTICITY (GPA DRY)
19

AVAILABILITY
WIDELY

MODULUS OF RUPTURE (MPA DRY)
144

FINISH
GOOD

SCREWING SPLIT RESISTANCE
GOOD

GROWING REGION
AUSTRALIA

TANGENTIAL SHRINKAGE
7%

SAPWOOD LYCTID SUSCEPTIBLE
NO

RADIAL SHRINKAGE
4%

DURABILITY
DURABLE

NAILING SPLIT RESISTANCE
GOOD

SPECIFIC GRAVITY
0.90

STABILITY
GOOD

BAL
29.0