

BLUE GUM



APPLICATIONS
DECKING & CLADDING JOINERY FLOORING

DENSITY
850

REGION
AUSTRALIA

Heartwood dark pink to red brown. Sapwood usually sufficiently paler to be readily distinguished. Texture moderately coarse and even. Grains straight or slightly interlocked. Gum veins common. Also known as Sydney Blue Gum.



PROPERTIES

DENSITY
850

HARDNESS (JANKA) (KN)
9.0

MACHINING
GOOD

GLUING
GOOD

MODULUS OF ELASTICITY (GPA DRY)
18

AVAILABILITY
WIDELY

MODULUS OF RUPTURE (MPA DRY)
140

FINISH
GOOD

SCREWING SPLIT RESISTANCE
GOOD

GROWING REGION
AUSTRALIA

TANGENTIAL SHRINKAGE
9%

SAPWOOD LYCTID SUSCEPTIBLE
YES

RADIAL SHRINKAGE
5%

DURABILITY
DURABLE

NAILING SPLIT RESISTANCE
GOOD

SPECIFIC GRAVITY
0.85

STABILITY
GOOD