

# CAMBIA ASH



## APPLICATIONS

FLOORING FURNITURE CABINETRY JOINERY DECKING & CLADDING

## DENSITY

675

## REGION

NORTH AMERICA

The Cambia thermal modification process uses high heat to improve its dimensional stability and decay resistance giving it a rich brown colour. Cambia products are more dimensionally stable and less prone to cup, warp and twist. Cambia does not contain any toxic chemicals.



## PROPERTIES

### DENSITY

675

### HARDNESS (JANKA) (KN)

6.0

### MACHINING

GOOD

### GLUING

GOOD

### MODULUS OF ELASTICITY (GPA DRY)

12

### AVAILABILITY

WIDELY

### MODULUS OF RUPTURE (MPA DRY)

104

### FINISH

EXCELLENT

### SCREWING SPLIT RESISTANCE

FAIR

### GROWING REGION

NORTH AMERICA

### TANGENTIAL SHRINKAGE

7%

### SAPWOOD LYCTID SUSCEPTIBLE

NO

### RADIAL SHRINKAGE

4%

### DURABILITY

DURABLE

### NAILING SPLIT RESISTANCE

FAIR

### SPECIFIC GRAVITY

0.60

### STABILITY

EXCELLENT