

CAMBIA OAK



APPLICATIONS
FURNITURE CABINETRY JOINERY FLOORING DECKING & CLADDING

DENSITY
705

REGION
NORTH AMERICA

The Cambia thermal modification process uses high heat to improve its dimensional stability and decay resistance giving it a rich brown colour. Cambia products are more dimensionally stable and less prone to cup, warp and twist. Cambia does not contain any toxic chemicals.



PROPERTIES

DENSITY 705	MODULUS OF RUPTURE (MPA DRY) 99	RADIAL SHRINKAGE 3%
HARDNESS (JANKA) (KN) 6.0	FINISH EXCELLENT	DURABILITY DURABLE
MACHINING GOOD	SCREWING SPLIT RESISTANCE FAIR	NAILING SPLIT RESISTANCE FAIR
GLUING GOOD	GROWING REGION NORTH AMERICA	SPECIFIC GRAVITY 0.64
MODULUS OF ELASTICITY (GPA DRY) 12	TANGENTIAL SHRINKAGE 5%	STABILITY EXCELLENT
AVAILABILITY AVAILABLE	SAPWOOD LYCTID SUSCEPTIBLE NO	