

CELERY TOP PINE



APPLICATIONS

FURNITURE CABINETRY JOINERY FLOORING DECKING & CLADDING BOATING

DENSITY

650

REGION

TASMANIA

The heartwood colour is pale yellow, with clearly defined growth rings. It is straight grained, with a fine, even texture. No taste or odour. Also known as Celery Top, Tasmanian Celery Top Pine.



PROPERTIES

DENSITY

650

HARDNESS (JANKA) (KN)

4.5

MACHINING

EXCELLENT

GLUING

GOOD

MODULUS OF ELASTICITY (GPA DRY)

10

AVAILABILITY

AVAILABLE

MODULUS OF RUPTURE (MPA DRY)

98

FINISH

EXCELLENT

SCREWING SPLIT RESISTANCE

EXCELLENT

GROWING REGION

TASMANIA

TANGENTIAL SHRINKAGE

3.5%

SAPWOOD LYCTID SUSCEPTIBLE

NO

RADIAL SHRINKAGE

1.5%

DURABILITY

DURABLE

NAILING SPLIT RESISTANCE

EXCELLENT

SPECIFIC GRAVITY

0.64

STABILITY

EXCELLENT