

# DAMAR MINYAK



## APPLICATIONS

FURNITURE CABINETS JOINERY FLOORING BOATING

## DENSITY

550

## REGION

ASIA PACIFIC

Heartwood pale yellowish brown, sometimes with a pinkish tinge. Sapwood often hard to distinguish from the heartwood. Texture very fine and even. Grain straight. No figure. Free of brittleheart. Also known as East Indian Kauri, Indonesian Kauri.

## PROPERTIES

### DENSITY

550

### HARDNESS (JANKA) (KN)

3.0

### MACHINING

EXCELLENT

### GLUING

GOOD

### MODULUS OF ELASTICITY (GPA DRY)

12

### AVAILABILITY

WIDELY

### MODULUS OF RUPTURE (MPA DRY)

67

### FINISH

EXCELLENT

### SCREWING SPLIT RESISTANCE

EXCELLENT

### GROWING REGION

ASIA PACIFIC

### TANGENTIAL SHRINKAGE

3%

### SAPWOOD LYCTID SUSCEPTIBLE

NO

### RADIAL SHRINKAGE

1.5%

### DURABILITY

NON DURABLE

### NAILING SPLIT RESISTANCE

EXCELLENT

### SPECIFIC GRAVITY

0.50

### STABILITY

GOOD