

# DURIAN



## APPLICATIONS

FURNITURE CABINETRY JOINERY FLOORING

## DENSITY

650

## REGION

ASIA PACIFIC

Sapwood is only moderately well defined in Coelostegia but well defined in Durio and Neesia. Heartwood is pink brown, grey brown, brown with a red tinge or light orange brown. Grain is straight to slightly interlocked. Texture is moderately coarse and even in Neesia but uneven in Durio and Coelostegia.



## PROPERTIES

### DENSITY

650

### HARDNESS (JANKA) (KN)

6.0

### MACHINING

GOOD

### GLUING

FAIR

### MODULUS OF ELASTICITY (GPA DRY)

16

### AVAILABILITY

AVAILABLE

### MODULUS OF RUPTURE (MPA DRY)

95

### FINISH

GOOD

### SCREWING SPLIT RESISTANCE

FAIR

### GROWING REGION

ASIA PACIFIC

### TANGENTIAL SHRINKAGE

4%

### SAPWOOD LYCTID SUSCEPTIBLE

YES

### RADIAL SHRINKAGE

2.5%

### DURABILITY

NON DURABLE

### NAILING SPLIT RESISTANCE

GOOD

### SPECIFIC GRAVITY

0.65

### STABILITY

GOOD