

EUROPEAN MAPLE



APPLICATIONS
FURNITURE CABINETRY JOINERY FLOORING BOATING

DENSITY
610

REGION
EUROPE

Heartwood creamy, darkening on exposure. Sapwood not clearly separated. Texture fine and even. Grain sometimes wavy, producing a fiddleback figure. Also known as Sycamore.



PROPERTIES

DENSITY 610	MODULUS OF RUPTURE (MPA DRY) 99	RADIAL SHRINKAGE 2%
HARDNESS (JANKA) (KN) 5.0	FINISH EXCELLENT	DURABILITY NON DURABLE
MACHINING GOOD	SCREWING SPLIT RESISTANCE EXCELLENT	NAILING SPLIT RESISTANCE EXCELLENT
GLUING EXCELLENT	GROWING REGION EUROPE	SPECIFIC GRAVITY 0.61
MODULUS OF ELASTICITY (GPA DRY) 10	TANGENTIAL SHRINKAGE 4%	STABILITY GOOD
AVAILABILITY WIDELY	SAPWOOD LYCTID SUSCEPTIBLE YES	