


HUON PINE



APPLICATIONS

FURNITURE CABINETRY JOINERY BOATING

DENSITY

520

REGION

TASMANIA

Heartwood pale straw, becoming yellow after long exposure. Sapwood very narrow and hard to distinguish. Texture very fine and even. Grain straight. Growth rings closely spaced. A characteristic odour, due to the essential oil methyl eugenol, present when wood freshly cut. Material with a birds-eye figure is sometimes obtainable.

PROPERTIES

DENSITY

520

MACHINING

EXCELLENT

GLUING

FAIR

AVAILABILITY

LIMITED

FINISH

EXCELLENT

SCREWING SPLIT RESISTANCE

EXCELLENT

GROWING REGION

TASMANIA

TANGENTIAL SHRINKAGE

3%

SAPWOOD LYCTID SUSCEPTIBLE

NO

RADIAL SHRINKAGE

2.5%

DURABILITY

DURABLE

NAILING SPLIT RESISTANCE

EXCELLENT

STABILITY

EXCELLENT