


IRONBARK GREY



APPLICATIONS

FURNITURE CABINETRY JOINERY FLOORING DECKING & CLADDING BOATING

DENSITY

1120

REGION

AUSTRALIA

Heartwood colour varies from pale brown to dark chocolate brown and also dark red. Texture moderately coarse and even. Grain usually interlocked.



PROPERTIES

DENSITY	MODULUS OF RUPTURE (MPA DRY)	RADIAL SHRINKAGE
1120	181	4.5%
HARDNESS (JANKA) (KN)	FINISH	DURABILITY
14.0	FAIR	DURABLE
MACHINING	SCREWING SPLIT RESISTANCE	NAILING SPLIT RESISTANCE
FAIR	FAIR	FAIR
GLUING	GROWING REGION	SPECIFIC GRAVITY
POOR	AUSTRALIA	1.10
MODULUS OF ELASTICITY (GPA DRY)	TANGENTIAL SHRINKAGE	STABILITY
24	8%	FAIR
AVAILABILITY	SAPWOOD LYCTID SUSCEPTIBLE	BAL
LIMITED	NO	29.0