

IRONBARK RED



APPLICATIONS

FURNITURE CABINETRY JOINERY FLOORING DECKING & CLADDING BOATING

DENSITY

1130

REGION

AUSTRALIA

Heartwood dark red. Sapwood pale yellow. Texture medium and even. Grain interlocked.



PROPERTIES

DENSITY

1130

HARDNESS (JANKA) (KN)

13.0

MACHINING

FAIR

GLUING

POOR

MODULUS OF ELASTICITY (GPA DRY)

17

AVAILABILITY

LIMITED

MODULUS OF RUPTURE (MPA DRY)

135

FINISH

FAIR

SCREWING SPLIT RESISTANCE

FAIR

GROWING REGION

AUSTRALIA

TANGENTIAL SHRINKAGE

7%

SAPWOOD LYCTID SUSCEPTIBLE

YES

RADIAL SHRINKAGE

3.5%

DURABILITY

DURABLE

NAILING SPLIT RESISTANCE

FAIR

SPECIFIC GRAVITY

1.10

STABILITY

FAIR

BAL

29.0