

JARRAH



APPLICATIONS

FURNITURE CABINETS JOINERY FLOORING DECKING & CLADDING BOATING

DENSITY

820

REGION

AUSTRALIA

Heartwood is a rich dark brownish red, sometimes marked by short, dark brown radial flecks on the end grain and boat shaped flecks on flat sawn surfaces which enhance its decorative value. The grain is usually straight but often interlocked or wavy. The texture is even but moderately coarse. Also known as Western Australian Jarrah.



PROPERTIES

DENSITY

820

HARDNESS (JANKA) (KN)

8.0

MACHINING

FAIR

GLUING

GOOD

MODULUS OF ELASTICITY (GPA DRY)

13

AVAILABILITY

WIDELY

MODULUS OF RUPTURE (MPA DRY)

112

FINISH

GOOD

SCREWING SPLIT RESISTANCE

FAIR

GROWING REGION

AUSTRALIA

TANGENTIAL SHRINKAGE

8%

SAPWOOD LYCTID SUSCEPTIBLE

YES

RADIAL SHRINKAGE

5%

DURABILITY

DURABLE

NAILING SPLIT RESISTANCE

FAIR

SPECIFIC GRAVITY

0.80

STABILITY

GOOD