

KARRI



APPLICATIONS
FURNITURE CABINETS JOINERY FLOORING DECKING & CLADDING BOATING

DENSITY
900

REGION
AUSTRALIA

Heartwood is reddish brown, paler in colour than Jannah when fresh, but maturing to a more uniform brown. The grain is interlocked with some wavy grain, the texture is even and moderately coarse. Also known as Western Australian Karri.



PROPERTIES

DENSITY
900

HARDNESS (JANKA) (KN)
9.0

MACHINING
FAIR

GLUING
FAIR

MODULUS OF ELASTICITY (GPA DRY)
19

AVAILABILITY
WIDELY

MODULUS OF RUPTURE (MPA DRY)
132

FINISH
GOOD

SCREWING SPLIT RESISTANCE
FAIR

GROWING REGION
AUSTRALIA

TANGENTIAL SHRINKAGE
10%

SAPWOOD LYCTID SUSCEPTIBLE
NO

RADIAL SHRINKAGE
4.5%

DURABILITY
DURABLE

NAILING SPLIT RESISTANCE
FAIR

SPECIFIC GRAVITY
0.88

STABILITY
GOOD