

# MELUNAK



**APPLICATIONS**  
**FURNITURE CABINETRY JOINERY FLOORING**

**DENSITY**  
**755**

**REGION**  
**ASIA PACIFIC**

Sapwood is moderately well defined. Heartwood is brown with a red or pink tinge or red brown. Grain is shallow to deeply interlocked. Texture is moderately fine and even.



## PROPERTIES

<b>DENSITY</b> <b>755</b>	<b>MODULUS OF RUPTURE (MPA DRY)</b> <b>85</b>	<b>RADIAL SHRINKAGE</b> <b>1.4%</b>
<b>HARDNESS (JANKA) (KN)</b> <b>7.0</b>	<b>FINISH</b> <b>GOOD</b>	<b>DURABILITY</b> <b>DURABLE</b>
<b>MACHINING</b> <b>FAIR</b>	<b>SCREWING SPLIT RESISTANCE</b> <b>GOOD</b>	<b>NAILING SPLIT RESISTANCE</b> <b>GOOD</b>
<b>GLUING</b> <b>FAIR</b>	<b>GROWING REGION</b> <b>ASIA PACIFIC</b>	<b>SPECIFIC GRAVITY</b> <b>0.75</b>
<b>MODULUS OF ELASTICITY (GPA DRY)</b> <b>12</b>	<b>TANGENTIAL SHRINKAGE</b> <b>2.5%</b>	<b>STABILITY</b> <b>GOOD</b>
<b>AVAILABILITY</b> <b>AVAILABLE</b>	<b>SAPWOOD LYCTID SUSCEPTIBLE</b> <b>NO</b>	