

MERANTI LIGHT RED



APPLICATIONS
FURNITURE CABINETS JOINERY

DENSITY
400

REGION
ASIA PACIFIC

Heartwood is pale to mid red-brown. Sapwood yellow, pink or grey and usually distinguishable. Texture coarse but even. Grain interlocked, usually giving a ribbon or strip figure to the radial surface.



PROPERTIES

DENSITY 400	MODULUS OF RUPTURE (MPA DRY) 66	RADIAL SHRINKAGE 2.8%
HARDNESS (JANKA) (KN) 2.0	FINISH GOOD	DURABILITY NON DURABLE
MACHINING GOOD	SCREWING SPLIT RESISTANCE GOOD	NAILING SPLIT RESISTANCE GOOD
GLUING GOOD	GROWING REGION ASIA PACIFIC	SPECIFIC GRAVITY 0.4
MODULUS OF ELASTICITY (GPA DRY) 9	TANGENTIAL SHRINKAGE 5.1%	STABILITY GOOD
AVAILABILITY WIDELY	SAPWOOD LYCTID SUSCEPTIBLE YES	