

# NORTHERN BOX



**APPLICATIONS**  
**DECKING & CLADDING**

**DENSITY**  
**900**

**REGION**  
**ASIA PACIFIC**

Sapwood yellow, tinged with red, merging into pink brown or red brown heartwood. Texture fine, even. Grain interlocked. Pores filled with gummy solid deposits. Wood is siliceous, with no distinct odour. Timber does not leach. Also known as Pelawan.

## PROPERTIES

<b>DENSITY</b> <b>900</b>	<b>MODULUS OF RUPTURE (MPA DRY)</b> <b>123</b>	<b>RADIAL SHRINKAGE</b> <b>5%</b>
<b>HARDNESS (JANKA) (KN)</b> <b>10.0</b>	<b>FINISH</b> <b>FAIR</b>	<b>DURABILITY</b> <b>DURABLE</b>
<b>MACHINING</b> <b>FAIR</b>	<b>SCREWING SPLIT RESISTANCE</b> <b>FAIR</b>	<b>NAILING SPLIT RESISTANCE</b> <b>FAIR</b>
<b>GLUING</b> <b>POOR</b>	<b>GROWING REGION</b> <b>ASIA PACIFIC</b>	<b>SPECIFIC GRAVITY</b> <b>0.90</b>
<b>MODULUS OF ELASTICITY (GPA DRY)</b> <b>15</b>	<b>TANGENTIAL SHRINKAGE</b> <b>10%</b>	<b>STABILITY</b> <b>FAIR</b>
<b>AVAILABILITY</b> <b>AVAILABLE</b>	<b>SAPWOOD LYCTID SUSCEPTIBLE</b> <b>NO</b>	