

PENINSULA ASH



APPLICATIONS

DENSITY
550

REGION
ASIA PACIFIC

Heartwood white to pale yellow-brown, darkening on exposure. Grain is shallowly interlocked and wavy. Texture medium and even. Lustrous, with faint ribbon figure on the quarter sawn face. Sapwood not well demarcated and white. Resin content present. Growth rings not apparent.



PROPERTIES

DENSITY 550	MODULUS OF RUPTURE (MPA DRY) 81	RADIAL SHRINKAGE 1.5%
HARDNESS (JANKA) (KN) 3.2	FINISH GOOD	DURABILITY NO
MACHINING POOR	SCREWING SPLIT RESISTANCE POOR	NAILING SPLIT RESISTANCE POOR
GLUING GOOD	GROWING REGION ASIA PACIFIC	SPECIFIC GRAVITY 0.50
MODULUS OF ELASTICITY (GPA DRY) 10	TANGENTIAL SHRINKAGE 2.5%	STABILITY GOOD
AVAILABILITY AVAILABLE	SAPWOOD LYCTID SUSCEPTIBLE YES	