

RIVER RED GUM

**APPLICATIONS**

FURNITURE CABINETS JOINERY FLOORING DECKING & CLADDING

DENSITY

900

REGION

AUSTRALIA

The heartwood varies according to location in age, from pink to dark red. The grain is interlocked and frequently wavy which produces a fiddleback figure when quarter cut. The texture is close and even. The wood is resinous with frequent gum pockets. The surface is often distinctly mottled. Also known as Murray Red Gum.

PROPERTIES

DENSITY

900

HARDNESS (JANKA) (KN)

10.0

MACHINING

FAIR

GLUING

FAIR

MODULUS OF ELASTICITY (GPA DRY)

11

AVAILABILITY

AVAILABLE

MODULUS OF RUPTURE (MPA DRY)

101

FINISH

GOOD

SCREWING SPLIT RESISTANCE

FAIR

GROWING REGION

AUSTRALIA

TANGENTIAL SHRINKAGE

4%

SAPWOOD LYCTID SUSCEPTIBLE

YES

RADIAL SHRINKAGE

2.5%

DURABILITY

DURABLE

NAILING SPLIT RESISTANCE

FAIR

SPECIFIC GRAVITY

0.90

STABILITY

GOOD

BAL

29.0