

ROSE GUM



APPLICATIONS

FURNITURE CABINETS JOINERY FLOORING DECKING & CLADDING BOATING

DENSITY

700

REGION

AUSTRALIA

Heartwood pink to pale red brown. Sapwood not always clearly differentiated. Texture moderately coarse but even. Grain straight. Also known as Flooded Gum.



PROPERTIES

DENSITY

700

HARDNESS (JANKA) (KN)

8.0

MACHINING

GOOD

GLUING

GOOD

MODULUS OF ELASTICITY (GPA DRY)

17

AVAILABILITY

AVAILABLE

MODULUS OF RUPTURE (MPA DRY)

122

FINISH

GOOD

SCREWING SPLIT RESISTANCE

GOOD

GROWING REGION

AUSTRALIA

TANGENTIAL SHRINKAGE

7%

SAPWOOD LYCTID SUSCEPTIBLE

NO

RADIAL SHRINKAGE

4%

DURABILITY

DURABLE

NAILING SPLIT RESISTANCE

GOOD

SPECIFIC GRAVITY

0.70

STABILITY

GOOD