

ROSEWOOD

**APPLICATIONS****FURNITURE CABINETRY JOINERY FLOORING DECKING & CLADDING BOATING****DENSITY****650****REGION****ASIA PACIFIC**

Heartwood can be either golden brown or a dark blood red. Sapwood pale yellow. Texture medium. Grain variable. The freshly cut wood has a fragrant odour often highly figured. Also known as New Guinea Rosewood, Solomon Islands Rosewood.

PROPERTIES

DENSITY**650****HARDNESS (JANKA) (KN)****5.0****MACHINING****EXCELLENT****GLUING****GOOD****MODULUS OF ELASTICITY (GPA DRY)****12****AVAILABILITY****AVAILABLE****MODULUS OF RUPTURE (MPA DRY)****95****FINISH****EXCELLENT****SCREWING SPLIT RESISTANCE****GOOD****GROWING REGION****ASIA PACIFIC****TANGENTIAL SHRINKAGE****2%****SAPWOOD LYCTID SUSCEPTIBLE****NO****RADIAL SHRINKAGE****1%****DURABILITY****DURABLE****NAILING SPLIT RESISTANCE****GOOD****SPECIFIC GRAVITY****0.65****STABILITY****EXCELLENT**