

SAPELE



APPLICATIONS FURNITURE CABINETRY JOINERY BOATING

Heartwood is pink when freshly cut to red brown or purple brown. Sapwood grey pink or cream. Interlocked grain producing a narrow and uniformly distributed stripe on the radial surface. Texture fine and even. The wood has a slight cedar like odour when freshly cut. Also known as Sapeli, Sapelli, Sapelle.

PROPERTIES

DENSITY 690 HARDNESS (JANKA) (KN) 7.0 MACHINING GOOD GLUING GOOD MODULUS OF ELASTICITY (GPA DRY) 12 AVAILABILITY WIDELY MODULUS OF RUPTURE (MPA DRY) 110 FINISH EXCELLENT SCREWING SPLIT RESISTANCE GOOD GROWING REGION AFRICA TANGENTIAL SHRINKAGE 4% SAPWOOD LYCTID SUSCEPTIBLE YES RADIAL SHRINKAGE **2%**

DURABILITY DURABLE

690

NAILING SPLIT RESISTANCE

PECIFIC GRAVITY

0.62 STABILITY

GOOD



