

SILVERTOP ASH



APPLICATIONS
FURNITURE JOINERY FLOORING DECKING & CLADDING

DENSITY
850

REGION
AUSTRALIA

Straight-grained timber that often features gum veins, ambrosia, growth rings and pencil steaks which add individuality to any project. The colour palette ranges from pale to medium browns with a hint of pink. Provides good fire resistance. .



PROPERTIES

DENSITY
850

HARDNESS (JANKA) (KN)
9.0

MACHINING
GOOD

GLUING
GOOD

MODULUS OF ELASTICITY (GPA DRY)
17

AVAILABILITY
AVAILABLE

MODULUS OF RUPTURE (MPA DRY)
136

FINISH
GOOD

SCREWING SPLIT RESISTANCE
FAIR

GROWING REGION
AUSTRALIA

TANGENTIAL SHRINKAGE
10.6%

SAPWOOD LYCTID SUSCEPTIBLE
NO

RADIAL SHRINKAGE
5%

DURABILITY
DURABLE

NAILING SPLIT RESISTANCE
FAIR

SPECIFIC GRAVITY
0.68

STABILITY
GOOD

BAL
29.0