

SPOTTED GUM

**APPLICATIONS**

FURNITURE CABINETRY JOINERY FLOORING DECKING & CLADDING

DENSITY

950

REGION

AUSTRALIA

Heartwood pale to dark brown or chocolate. Sapwood is distinctively paler but there may be a zone of intermediate wood. Texture moderately coarse. Grain variable, the frequent presence of wavy grain produces an attractive fiddleback figure. Slightly greasy nature. Gum veins common. Northern material is usually slightly denser, stronger and more durable than southern. Also known as Lemon Scented Gum.



PROPERTIES

DENSITY 950	MODULUS OF RUPTURE (MPA DRY) 150	RADIAL SHRINKAGE 4.5%
HARDNESS (JANKA) (KN) 11.0	FINISH GOOD	DURABILITY DURABLE
MACHINING GOOD	SCREWING SPLIT RESISTANCE GOOD	NAILING SPLIT RESISTANCE GOOD
GLUING POOR	GROWING REGION AUSTRALIA	SPECIFIC GRAVITY 0.95
MODULUS OF ELASTICITY (GPA DRY) 23	TANGENTIAL SHRINKAGE 6%	STABILITY FAIR
AVAILABILITY AVAILABLE	SAPWOOD LYCTID SUSCEPTIBLE YES	BAL 29.0