

## SURIAN



APPLICATIONS

JOINERY

DENSITY

REGION

ASIA PACIFIC

Heartwood reddish brown. Sapwood narrow, pale red and distinctive. Texture moderately coarse. Grain often interlocked. Characteristic cedar odour. The wood is very similar to that of Australian red cedar. Also known as Kalantas, Red Cedar.



## PROPERTIES

DENSITY

480

HARDNESS (JANKA) (KN)

2.0

MACHINING

GOOD

GLUING FAIR

MODULUS OF ELASTICITY (GPA DRY)

**AVAILABILI** 

**AVAILABLE** 

MODULUS OF RUPTURE (MPA DRY)

65

FINIS

**EXCELLENT** 

SCREWING SPLIT RESISTANCE

GOOD

**GROWING REGION** 

**ASIA PACIFIC** 

TANGENTIAL SHRINKAGE

**7**%

SAPWOOD LYCTID SUSCEPTIBLE

YES

4%

DURABILITY

**DURABLE** 

NAILING SPLIT RESISTANCE

GOOD

SPECIFIC GRAVITY

0.45

STABILITY

GOOD