

TALLOWWOOD



APPLICATIONS
FURNITURE CABINETRY JOINERY FLOORING DECKING & CLADDING BOATING

DENSITY
990

REGION
AUSTRALIA

Heartwood yellowish brown with a tinge of olive green. Sapwood usually distinctively paler. Texture moderately coarse but even. Grain often interlocked. The wood has a greasy feel and can effect the strength of the bond obtainable with adhesives. An unusual distinguishing characteristic for a eucalypt, is the complete absence of gum veins.



PROPERTIES

DENSITY 990	MODULUS OF RUPTURE (MPA DRY) 134	RADIAL SHRINKAGE 4%
HARDNESS (JANKA) (KN) 9.0	FINISH GOOD	DURABILITY DURABLE
MACHINING GOOD	SCREWING SPLIT RESISTANCE GOOD	NAILING SPLIT RESISTANCE GOOD
GLUING POOR	GROWING REGION AUSTRALIA	SPECIFIC GRAVITY 0.99
MODULUS OF ELASTICITY (GPA DRY) 18	TANGENTIAL SHRINKAGE 6%	STABILITY GOOD
AVAILABILITY LIMITED	SAPWOOD LYCTID SUSCEPTIBLE YES	