

TASMANIAN MYRTLE



APPLICATIONS
FLOORING FURNITURE CABINETS JOINERY

DENSITY
700

REGION
TASMANIA

Rich red to reddish brown coloured heartwood, paler sapwood separated from the heartwood by a zone of intermediate colour. The grain is straight to slightly interlocked, sometimes wavy and the texture is very fine and uniform. Also known as Beech, Myrtle.



PROPERTIES

DENSITY 700	MODULUS OF RUPTURE (MPA DRY) 108	RADIAL SHRINKAGE 2.5%
HARDNESS (JANKA) (KN) 6.0	FINISH GOOD	DURABILITY NON DURABLE
MACHINING GOOD	SCREWING SPLIT RESISTANCE GOOD	NAILING SPLIT RESISTANCE GOOD
GLUING GOOD	GROWING REGION TASMANIA	SPECIFIC GRAVITY 0.72
MODULUS OF ELASTICITY (GPA DRY) 14	TANGENTIAL SHRINKAGE 4.5%	STABILITY GOOD
AVAILABILITY LIMITED	SAPWOOD LYCTID SUSCEPTIBLE YES	