

# VICTORIAN ASH



**APPLICATIONS**  
FURNITURE CABINETRY JOINERY FLOORING BOATING

**DENSITY**  
680

**REGION**  
AUSTRALIA

Heartwood pale pink or pale straw. Sapwood not always clearly differentiated. Texture rather coarse. Grain straight. Growth rings conspicuous. Gum veins common. Also known as Mountain Ash, Alpine Ash.



## PROPERTIES

<b>DENSITY</b> 680	<b>MODULUS OF RUPTURE (MPA DRY)</b> 110	<b>RADIAL SHRINKAGE</b> 3.5%
<b>HARDNESS (JANKA) (KN)</b> 5.0	<b>FINISH</b> GOOD	<b>DURABILITY</b> NON DURABLE
<b>MACHINING</b> GOOD	<b>SCREWING SPLIT RESISTANCE</b> GOOD	<b>NAILING SPLIT RESISTANCE</b> GOOD
<b>GLUING</b> GOOD	<b>GROWING REGION</b> AUSTRALIA	<b>SPECIFIC GRAVITY</b> 0.70
<b>MODULUS OF ELASTICITY (GPA DRY)</b> 15	<b>TANGENTIAL SHRINKAGE</b> 8.5%	<b>STABILITY</b> GOOD
<b>AVAILABILITY</b> WIDELY	<b>SAPWOOD LYCTID SUSCEPTIBLE</b> YES	