


WENGE



APPLICATIONS

FURNITURE CABINETRY JOINERY FLOORING BOATING

DENSITY

910

REGION

AFRICA

The clearly defined heartwood is dark brown, with very close, fine, almost black veins. The closely spaced whitish bands parenchyma give the wood a most attractive appearance. It is fairly straight grained with a coarse texture.

PROPERTIES

DENSITY	MODULUS OF RUPTURE (MPA DRY)	RADIAL SHRINKAGE
910	152	3%
HARDNESS (JANKA) (KN)	FINISH	DURABILITY
10.0	GOOD	DURABLE
MACHINING	SCREWING SPLIT RESISTANCE	NAILING SPLIT RESISTANCE
GOOD	FAIR	FAIR
GLUING	GROWING REGION	SPECIFIC GRAVITY
FAIR	AFRICA	0.74
MODULUS OF ELASTICITY (GPA DRY)	TANGENTIAL SHRINKAGE	STABILITY
16	6%	GOOD
AVAILABILITY	SAPWOOD LYCTID SUSCEPTIBLE	
AVAILABLE	NO	