


# WESTERN RED CEDAR



**APPLICATIONS**  
**CABINETSRY DECKING & CLADDING JOINERY**

**DENSITY**  
**380**

**REGION**  
**NORTH AMERICA**

Heartwood variable, from pale brown to dark brown. Sapwood is yellowish white. Texture fine but uneven due to the prominent growth rings. Grain straight. Not resinous. Also known as Red Cedar, American Cedar.



## PROPERTIES

<b>DENSITY</b> <b>380</b>	<b>MODULUS OF RUPTURE (MPA DRY)</b> <b>54</b>	<b>RADIAL SHRINKAGE</b> <b>1.5%</b>
<b>HARDNESS (JANKA) (KN)</b> <b>2.0</b>	<b>FINISH</b> <b>GOOD</b>	<b>DURABILITY</b> <b>DURABLE</b>
<b>MACHINING</b> <b>GOOD</b>	<b>SCREWING SPLIT RESISTANCE</b> <b>GOOD</b>	<b>NAILING SPLIT RESISTANCE</b> <b>GOOD</b>
<b>GLUING</b> <b>GOOD</b>	<b>GROWING REGION</b> <b>NORTH AMERICA</b>	<b>SPECIFIC GRAVITY</b> <b>0.38</b>
<b>MODULUS OF ELASTICITY (GPA DRY)</b> <b>8</b>	<b>TANGENTIAL SHRINKAGE</b> <b>3%</b>	<b>STABILITY</b> <b>EXCELLENT</b>
<b>AVAILABILITY</b> <b>WIDELY</b>	<b>SAPWOOD LYCTID SUSCEPTIBLE</b> <b>NO</b>	